



## TECHNICAL DATA SHEET

# KEIM CONCRETAL®-FIXATIV

## 1. PRODUCT DESCRIPTION

KEIM Concretal-Fixativ is a silicate-based dilution and primer developed for concrete substrates, its binder consisting of a combination of potassium silicate, silica sol and organic additives.

## 2. FIELD OF APPLICATION

KEIM Concretal-Fixativ is the dilution and additive for the silicate-based coatings in the KEIM Concretal concrete protection system:

KEIM Concretal-Black  
KEIM Concretal-W  
KEIM Concretal-W-Grob  
KEIM Concretal-Lasur  
KEIM Contact-Plus

The absorbency of highly absorbent mineral substrates can be controlled or reduced with KEIM Concretal-Fixativ.

## 3. PRODUCT PROPERTIES

- Bonds permanently with the substrate by silicification
- Weather resistant
- Water vapour permeable
- Non-flammable
- UV-resistant
- Hinders fungal and mould growth
- Resistant to industrial fumes
- Solvent-resistant
- Environmentally friendly, good environmental impact assessment
- Excellent low environmental impact building material

### Material characteristics:

- Specific weight: approx. 1.0 - 1.1 g/cm<sup>3</sup>
- pH-value: approx. 11

### Colour shades:

Milky

## 4. APPLICATION INSTRUCTIONS

### Substrate preparation:

The substrate must be sound, dry, clean and free from any

loose particles, dust, oil or other adhesion-impairing substances. Repair damaged areas using the KEIM Concretal concrete repair system.

### Application:

For pretreating highly absorbent substrates:  
Apply KEIM Concretal-Fixativ undiluted with a brush.

As dilution for normal smooth substrates for opaque protective coatings for concrete:

KEIM Concretal-W/Concretal-W-Grob/Concretal-Black  
For the priming coat, depending on substrate absorbency, stir at most 10% KEIM Concretal-Fixativ into KEIM Concretal-W (max. 2.5 litres of dilution per 25 kg of paint), finishing coat with undiluted KEIM Concretal-W/Concretal-Black.

### KEIM Concretal-Lasur:

For the priming coat, depending on substrate absorbency, stir approx. 20-50% KEIM Concretal-Fixativ into KEIM Concretal-Lasur (approx. 0.2-0.5 litre of dilution per liter of Lasur), finishing coat with undiluted KEIM Concretal-Lasur.

As a dilution for low-pigment/creative use:

Depending on the desired finish, KEIM Concretal-Lasur may be diluted in the priming and finishing coat with KEIM Concretal-Fixativ in any desired ratio.

See the relevant Technical Data Sheet for further details regarding the dilution and use of KEIM Concretal-W, Concretal-Black and KEIM Concretal-Lasur.

### Application conditions:

Ambient and substrate temperature > + 5 °C.

### Drying time:

A drying time of at least 12 hours must be allowed between pretreatment and priming and between coats.

### Consumption:

For pretreatment on a smooth substrate:  
Approx. 0.1 – 0.2 l/m<sup>2</sup> KEIM Concretal-Fixativ.

The stated consumption value is for guidance and depends on the absorbency and texture of the substrate. Exact consumption values can only be determined by painting test areas on the structure to be coated.

### Cleaning of tools:

Clean with water immediately after use.



### 5. PACKAGING

5 l and 20 l containers.

### 6. STORAGE

Storage life is approx. 12 months in a sealed container under cool, but frost-free conditions. Protect from heat and direct sunlight.

### 7. DISPOSAL

EC Waste Code No. 06 02 99

Any residues must be emptied out of containers before recycling.

### 8. SAFETY INSTRUCTIONS

Giscode: BSW10

KEIM Concretal-Fixativ is alkaline. Provide appropriate protection for surfaces which are not to be treated (e.g. glass, ceramics, wood etc.). Any splashes on surrounding surfaces or traffic areas must be rinsed off immediately with water. Protect the eyes and skin from splashes. Keep out of reach of children.

Please refer to EC Safety Data Sheet.

The stated values and properties are the result of extensive development work and practical experience. Our recommendations for application, whether given verbally or in writing, are intended to provide assistance in the selection of our products and do not establish a contractual relationship. In particular, they do not release those purchasing and applying our products from the duty of establishing for themselves, with due care, the suitability of our products for the intended application. Standard building industry practices must be complied with. We retain the right to make modifications to improve the products or their application. This edition supersedes all earlier editions.



KEIMFARBEN GMBH

Keimstraße 16 / 86420 Diedorf / Tel. +49 (0)821 4802-0 / Fax +49 (0)821 4802-210  
Frederik-Ipsen-Straße 6 / 15926 Luckau / Tel. +49 (0)35456 676-0 / Fax +49 (0)35456 676-38  
[www.keim.com/info@keimfarben.de](http://www.keim.com/info@keimfarben.de)