



TECHNICAL DATA SHEET

KEIM CONCRETAL®-W / -W-GROB

1. PRODUCT DESCRIPTION

Sol-silicate protective concrete paint as per DIN EN 1504-2 sect. 2.2, 8.2. KEIM Concretal-W- Grob is a filled variant of KEIM Concretal-W for priming coats.

2. FIELD OF APPLICATION

KEIM Concretal-W is used to protect concrete surfaces on exterior facades and interior concrete surfaces subjected to severe loads, e.g. in multistory car parks, with a protective action providing protection from water and weathering by silicification and protection from chloride. Water protection may be further enhanced by providing the substrate with a hydrophobic treatment using KEIM Silangrund or KEIM Silan- 100. The combination with KEIM Silan-100 provides „grade W protection“ according to Rili-SIB (guidelines for the protection and renovation of concrete components published by the German committee on steel reinforced concrete (DAfStb). Not suitable for horizontal and inclined surfaces exposed to weathering. KEIM Concretal-W-Grob is applied as a priming coat or as a priming and intermediate coat for equalising differences in structure and filling hairline cracks.

3. PRODUCT PROPERTIES

KEIM Concretal-W protects concrete from weathering and penetration of liquid water and, while simultaneously providing very good water vapour diffusion from inside to outside, it prevents water formation in the concrete and thus corrosion of the reinforcement steel (corrosion protection by keeping the concrete dry).

At the same time it prevents penetration of chloride salts and other pollutants. KEIM Concretal-W has a matt mineral finish and preserves concrete surface textures, such as cladding structures. Immobile hairline cracks can be filled in combination with KEIM Concretal-W-Grob. For production reasons, filled paint material (Concretal-W-Grob) is not suitable for finish coats because the colours are lighter than the original colour swatches. KEIM Concretal-W is non-flammable (class A2 according to DIN 4102/class A2-s 1, d0 according to EN 13501-1, compliant with classification report).

Colour shades:

White and according to the KEIM Palette Exclusiv colour swatches. Full-tone colours only available as 9001S – 9010S. Tinting only with the KEIM Concretal-W full-tone colours.

Binder:

Binder formulated with silica sol, potassium water glass and

pure acrylate.

Technical data:

- Density:	
Concretal-W	approx.1.5 - 1.8 g/cm ³
Concretal-W-Grob	approx.1.5 - 1.8 g/cm ³

Material characteristics acc. to DIN EN 1504:

- Water vapour diffusion resistance:	$s_d (H_2O) \leq 0.01 \text{ m}$
- Water absorption coefficient:	$w < 0.01 \text{ [kg/m}^2\text{h}^{0.5}]$
- Tensile strength T standard:	2.3 (1.4) N/mm ²
- Colour fastness:	A1 (Colour code acc. to BFS Technical information No 26)

4. APPLICATION INSTRUCTIONS

The substrate must be sound, dry, clean and free from any loose particles, dust, oil or other adhesion-impairing substances. Organically bound prior coats must be completely removed.

In the case of new concrete structures, any shuttering oil residues should be removed with KEIM Betonschnellreiniger. Clean, strong concrete requires no pretreatment. Before Concretal-W is applied, highly absorbent substrates or surfaces exposed to severe weather may be provided with a water-repellent substrate treatment using KEIM Silangrund or KEIM Silan-100 (tested to ZTV-ING) to enhance water protection. The subsequent primer coat of Concretal-W or Concretal-W-Grob may be applied after approx. 4 hours in the case of KEIM Silangrund and after 4 to 24 hours in the case of KEIM Silan-100. Soft, porous concrete surfaces or mineral prior coats may be stabilized by pretreatment with KEIM Concretal-Fixativ.

One or two priming coats of KEIM Concretal-W Grob may be applied to level surfaces and to fill immobile hairline cracks.

Application:

KEIM Concretal-W-Grob can be applied by paint brush or airless spraying. KEIM Concretal-W can be applied by brush, roller or airless spraying (KEIM Concretal-W: nozzle 435, KEIM Concretal-W-Grob: nozzle 443; see technical data sheet for „Airless Technique“ for further information).

Two-coat structure:

Base coat:
25 kg of KEIM Concretal-W or KEIM Concretal-W-Grob diluted with max. 2.5 l of KEIM Concretal-Fixativ.
Final coat:
KEIM Concretal-W undiluted.



Three-coat structure:

Priming coat:

25 kg of KEIM Concretal-W-Grob diluted with max. 2.5 l of KEIM Concretal-Fixativ.

Intermediate coat:

25 kg of KEIM Concretal-W-Grob diluted with max. 1.25 l of KEIM Concretal-Fixativ.

Final coat:

KEIM Concretal-W undiluted.

Stir diluted KEIM Concretal-W and KEIM Concretal-W-Grob before and during application. Neither water nor any other materials may be added.

Application conditions:

From +5 °C up to max. 30 °C air and substrate temperature, up to max. 80% relative humidity.

Only apply in dry weather conditions. Do not apply in strong sunlight, onto substrates heated by the sun or in strong wind. After application, protect surfaces from excessively fast drying, wind and rain.

Drying times:

At least 12 hours between coats; priming coat approx. 4 hours after a pretreatment with KEIM Silangrund or approx. 4-24 hours after KEIM Silan-100.

Consumption:

Two coats of KEIM Concretal-W:

0.35 kg/m² KEIM Concretal-W

0.02 l/ m² KEIM Concretal-Fixativ

Priming coat with KEIM Concretal-W Grob,

final coat with KEIM Concretal-W:

0.20 kg/ m² KEIM Concretal-W-Grob

0.20 kg/ m² KEIM Concretal-W

0.02 l/ m² KEIM Concretal-Fixativ

Three coats of KEIM Concretal-W:

0.45 kg/ m² KEIM Concretal-W

0.03 l/ m² KEIM Concretal-Fixativ

Priming and intermediate coat with KEIM Concretal-W-Grob, final coat with KEIM Concretal-W:

0.35 kg/ m² KEIM Concretal-W-Grob

0.20 kg/ m² KEIM Concretal-W

0.03 l/ m² KEIM Concretal-Fixativ

The stated consumption figures are guide values for a smooth substrate. Exact values can only be determined by painting test areas on the structure to be coated.

Dry film thickness:

100-150 µm with two coats of Concretal-W on a smooth substrate.

Consumption:

Clean with water immediately after use

5. PACKAGING

KEIM Concretal-W: 2.5kg, 5kg and 18 kg container

KEIM Concretal-W-Grob: 2.5kg, 5kg and 18 kg container

KEIM Concretal-Fixativ: 5 l and 20 l container

6. STORAGE

In a sealed container under cool, but frost-free conditions, KEIM Concretal-W, KEIM Concretal-W-Grob and KEIM Concretal-Fixativ have a storage life of 12 months.

7. DISPOSAL

EC Waste Code No. 08 01 12

Any residues must be emptied out of containers before recycling.

8. SAFETY INSTRUCTIONS

Giscode: BSW10

The mineral binder has an alkaline action. Provide appropriate protection for surfaces which are not to be coated (e.g. glass, natural stone, ceramics etc.). Any splashes on surrounding surfaces or traffic areas must be rinsed off immediately with plenty of water. Protect the eyes and skin from splashes. Keep out of reach of children.

Please refer to EC Safety Data Sheet.

9. CERTIFICATES & QUALITY SEALS



The stated values and properties are the result of extensive development work and practical experience. Our recommendations for application, whether given verbally or in writing, are intended to provide assistance in the selection of our products and do not establish a contractual relationship. In particular, they do not release those purchasing and applying our products from the duty of establishing for themselves, with due care, the suitability of our products for the intended application. Standard building industry practices must be complied with. We retain the right to make modifications to improve the products or their application. This edition supersedes all earlier editions. 9.



KEIMFARBEN GMBH

Keimstraße 16 / 86420 Diedorf / Tel. +49 (0)821 4802-0 / Fax +49 (0)821 4802-210
Frederik-Ipsen-Straße 6 / 15926 Luckau / Tel. +49 (0)35456 676-0 / Fax +49 (0)35456 676-38
www.keim.com/info@keimfarben.de